## ชื่อปริญญานิพนธ์เส้นโค้งความเค้นความเครียดของคอนกรีตมวลเบาแบบเซลลูล่า

โดย 1. นายวีระศักดิ์ พิมพ์มะษร

รหัสนักศึกษา 5413402241

2. นายนวพงษ์ นิลโชติ

รหัสนักศึกษา 5413405127

## บทคัดย่อ

ปริญญานิพนธ์นี้ศึกษาเส้นโค้งความเค้น-ความเครียดของคอนกรีตมวลเบาแบบเซลลูล่าที่ ความหนาแน่น 1,800 กิโลกรัมต่อลูกบาศก์เมตร ใช้ตัวอย่างรูปทรงกระบอกมาตรฐาน ขนาดเส้นผ่าน ศูนย์กลาง 15 เซนติเมตร สูง 30 เซนติเมตร ใช้วิธีการบ่มในอากาศมีทั้งหมด 9 สูตร ทดสอบที่อายุ 28 วัน และ 56 วัน ครั้งละ 25 ตัวอย่างและทดสอบโดยใช้เครื่องทดสอบแรงกด

จากผลการศึกษาเส้นโค้งความเค้น-ความเครียดของคอนกรีตมวลเบาแบบเซลลูล่าสรุปได้ว่า ความเครียดที่เกิดความเค้นสูงสุดอยู่ในช่วง 0.0028-0.0036 มีค่าเฉลี่ยอยู่ที่ 0.0032 และความเครียด ที่เกิดการวิบัติอยู่ในช่วง 0.0036-0.0045 มีค่าเฉลี่ยอยู่ที่ 0.0040 โดยที่ปริมาณน้ำมีแนวโน้มที่ไม่ แน่นอนต่อตำแหน่งความเครียดที่เกิดความเค้นสูงสุดและตำแหน่งความเครียดที่เกิดการวิบัติ ปริมาณ ทรายมีแนวโน้มที่ทำให้ตำแหน่งความเครียดที่เกิดความเค้นสูงสุดและตำแหน่งความเครียดที่เกิดการวิบัติ บัติลดลงเมื่อปริมาณทรายมากขึ้น แต่อายุคอนกรีตมีผลกระทบน้อยมากต่อตำแหน่งความเครียดที่ เกิดความเค้นสูงสุดและตำแหน่งความเครียดที่ เกิดการวิบัติ

## Project Title Stress-Strain Curve of Cellular Lightweight Concrete

By 1.Mr.Weerasak Pimmasorn ID 5413402241

2.Mr.Nawapong Nilchot ID 5413405127

## **ABSTRACT**

This project studied stress-strain curve of cellular lightweight concrete with a density of 1,800 kg/m<sup>3</sup>. The standard cylinders of diameter 15 centimeter and height of 30 centimeter were used and cured in the air. The testing programs of concrete specimens consist of 9 formulas for which 25 cylinders were cast and tested at 28 days and 56 days by a universal testing machine.

From the studies, it was found that stress-strain curve of cellular lightweight concrete reached the strain at maximum stress in a range of 0.0028 to 0.0036 with the average of 0.0032. In addition, the strain at failure was found in a range of 0.0036 to 0.0045 with the average of 0.0032. Furthermore, the effect of amount of water to the stress-strain curve of cellular lightweight concrete is inconclusive. However, the increase of sand has some effect on the strain at maximum stress and strain at failure as they had a tendency to decrease. Finally, the age of concrete has little or no effect on the stress-strain curve of cellular lightweight concrete.