

ชื่อปริญญา ni พนธ

“การศึกษาสัดส่วนผสมที่เหมาะสมในการผลิตบล็อกคอนกรีตมวลเบาแบบเซลลูโล่”

โดย นายศรavya จิรนัตรเจริญ รหัสประจำตัว 50138663
 นายอธิวัฒน์ ลาภาน รหัสประจำตัว 5113401357
 นายจักรวัล ศรีอินทร์ รหัสประจำตัว 5113413792
 นายเกิดพงษ์ สมใส รหัสประจำตัว 5113440736

บทคัดย่อ

โครงการนี้ศึกษาสัดส่วนผสมที่เหมาะสมในการผลิตบล็อกคอนกรีตมวลเบาแบบเซลลูโล่ที่ค่าหน่วยวันน้ำหนักออกแบบ 800, 900 และ 1,000 กิโลกรัมต่อลูกบาศก์เมตร โดยอัตราส่วนน้ำต่อปูนซีเมนต์เท่ากับ 0.35 ,0.45 และ 0.50 และใช้อัตราส่วนทรายต่อปูนซีเมนต์เท่ากับ 0.75, 1.0, 1.25 และ 1.5 รวมทั้งหมด 27 สูตรส่วนผสม ทดสอบกำลังรับแรงอัดและการดูดซึมน้ำของคอนกรีตมวลเบาแบบเซลลูโล่ที่อายุ 28 และ 56 วัน ของตัวอย่างทรงลูกบาศก์ รวมจำนวนตัวอย่างทั้งสิ้น 324 ตัวอย่าง ผลการศึกษาพบว่า ค่าหน่วยวันน้ำหนัก 800 กิโลกรัมต่อลูกบาศก์เมตร ที่อายุ 28 วัน ค่ากำลังรับแรงอัดระหว่าง 0.99 ถึง 5.13 กิโลกรัมต่อบาร์เซนติเมตร ที่อายุ 56 วัน ค่ากำลังรับแรงอัดระหว่าง 10.75 ถึง 16.96 กิโลกรัมต่อบาร์เซนติเมตร และค่าดูดซึมน้ำที่อายุ 28 วัน ค่าดูดซึมน้ำอยู่ระหว่าง 26.52 ถึง 44.71 เปอร์เซ็นต์ ที่อายุ 56 วัน ค่าดูดซึมน้ำอยู่ระหว่าง 39.11 ถึง 53.22 เปอร์เซ็นต์ ค่าหน่วยวันน้ำหนัก 900 กิโลกรัมต่อลูกบาศก์เมตร ที่อายุ 28 วัน ค่ากำลังรับแรงอัดระหว่าง 1.56 ถึง 6.68 กิโลกรัมต่อบาร์เซนติเมตร ที่อายุ 56 วัน ค่ากำลังรับแรงอัดระหว่าง 12.3 ถึง 18.99 กิโลกรัมต่อบาร์เซนติเมตร และค่าดูดซึมน้ำที่อายุ 28 วัน ค่าดูดซึมน้ำอยู่ระหว่าง 24.45 ถึง 43.68 เปอร์เซ็นต์ ที่อายุ 56 วัน ค่าดูดซึมน้ำอยู่ระหว่าง 7.3 ถึง 45.0 เปอร์เซ็นต์ ค่าหน่วยวันน้ำหนัก 1,000 กิโลกรัมต่อลูกบาศก์เมตร ที่อายุ 28 วัน ค่ากำลังรับแรงอัดระหว่าง 5.61 ถึง 14.66 กิโลกรัมต่อบาร์เซนติเมตร และค่าดูดซึมน้ำที่อายุ 28 วัน ค่าดูดซึมน้ำอยู่ระหว่าง 17.74 ถึง 38.26 เปอร์เซ็นต์ ที่อายุ 56 วัน ค่าดูดซึมน้ำอยู่ระหว่าง 1.31 ถึง 17.15 เปอร์เซ็นต์ โดยมาตราฐานอุตสาหกรรมที่ใช้เปรียบเทียบบล็อกคอนกรีตมวลเบาอยู่ที่ค่าหน่วยวันน้ำหนักที่เหมาะสม และควรนำมาพัฒนาเพื่อผลิตบล็อกคอนกรีตมวลเบาอยู่ที่หน่วยวันน้ำหนัก 1,000 กิโลกรัมต่อลูกบาศก์เมตร

Project Title

“Mix Proportion Cellular Lightweight Concrete Blocks.”

BY	Mr. Sarawut Jirasutjaroen	ID No. 50138663
	Mr. Atiwat Lapan	ID No. 5113401357
	Mr. Jakawal sri-in	ID No. 5113413792
	Mr. Tendpong somsai	ID No. 5113440736

Abstract

The objective of this project is to study the mix proportion of cellular lightweight concrete blocks with the designed unit weights of 800, 900 and 1,000 kilograms per cubicmetres. The water to cement ratio (W/C) used in this study were 0.35, 0.45 and 0.50 and the sand to cement ratio (S:C) of 0.75, 0.1, 1.25 and 1.5 were employed having a total of 27 design mixs. A total of 324 cube samples were produced for the compressive strength and water absorption test at age 28 and 56 days. The results show that the unit weight of 800 kilograms per cubicmetres at age 28 days gains the compressive strength in a range of 0.99 – 5.13 kilograms per cubicmetres and at age 56 days gains the compressive strength in a range 10.75 – 16.96 kilograms per cubicmetres. The water absorption at age 28 days is between 26.52 – 44.71 % and at age 56 day is between 39.11 – 53.22 %. For the unit weight of 900 kilograms per cubicmetres at age 28 days, the compressive strength is in a range of 1.56 – 6.68 kilograms per cubicmetres and at age 56 days, it is in a range of 12.3 – 18.99 kilograms per cubicmetres. The percentages of water absorption at age 28 days are in between 24.45 – 43.68 % and at age 56 day are in between 7.3 – 45.0 %. Lastly for the unit weight of 1,000 kilograms per cubicmetres at age 28 days, the compressive strength is in a range 5.61 – 14.66 kilograms per cubicmetres and at age 56 days. The compressive strength in a range 16.25 – 24.54 kilograms per cubicmetres. The percentages of water absorption at age 28 days are in between 17.74 – 38.26 % and at age 56 day are in between 1.31 – 17.15 %. The industry standard for concrete blocks requires that the compressive strength should not be less than 25 kilograms per cubicmetres and the water absorption not more than 40 percent of the weight. Therefor, the suitable unit weight to be developed for lightweight concrete blocks should be 1,000 kilograms per cubicmetres.